

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>A61K 7/035</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 97/04737</b> <b>(43) International Publication Date:</b> 13 February 1997 (13.02.97)
<b>(21) International Application Number:</b> PCT/US96/12247 <b>(22) International Filing Date:</b> 25 July 1996 (25.07.96)  <b>(30) Priority Data:</b> 08/509,488 31 July 1995 (31.07.95) US 08/629,293 8 April 1996 (08.04.96) US  <b>(71) Applicant:</b> THE PROCTER & GAMBLE COMPANY [US/US]; One Procter & Gamble Plaza, Cincinnati, OH 45202 (US).  <b>(72) Inventors:</b> LaFLEUR, Patricia, Alison; 15 Briarwood Road, Shewsbury Township, PA 17361 (US). VADAKETH, Leena; 18 Avignon Drive, Newark, DE 19702 (US). LEP- PLA, Jeffrey, Keith; 106 Upnor Road, Baltimore, MD 21212 (US).  <b>(74) Agents:</b> REED, T., David et al.; The Procter & Gamble Company, 5299 Spring Grove Avenue, Cincinnati, OH 45217 (US).		<b>(81) Designated States:</b> AU, CA, CN, CZ, JP, MX, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
<b>(54) Title:</b> COSMETIC POWDER COMPOSITIONS HAVING IMPROVED SKIN COVERAGE  <b>(57) Abstract</b>  The present invention is for powder compositions containing high levels of talc, low levels of titanium dioxide and a sebum absorbing material wherein the composition has improved skin coverage, uniformity and duration of wear. The invention can be used in formulating numerous cosmetic powder compositions such as eye shadow, foundation, loose powder and the like.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

COSMETIC POWDER COMPOSITIONS  
HAVING IMPROVED SKIN COVERAGE

5

## TECHNICAL FIELD

10       The present invention is for powder compositions with improved skin coverage and uniformity and duration of wear compared to previously formulated compositions. These compositions comprises high levels of selected talc, little or no titanium dioxide as a filler or extender and a sebum absorbing material. Said compositions can be formulated to form a variety of color cosmetic compositions including eye shadows, foundations and the like.

15

## BACKGROUND OF THE INVENTION

Color powder compositions for application to the skin, particularly the face and around the eyes are well known in the art. These compositions take a number of different forms ranging from loose powders in canisters to those that are molded or compressed into cakes and inserted into mirrored compact cases, typically supplied with an applicator, usually a pad, a puff or other  
20       implement.

These compositions comprise, in a major part, fillers and extenders, most of which are of the mineral variety. Examples of such mineral fillers and extenders include talc, kaolin, mica, silicon dioxide, silicon dioxide-coated mica and talc, titanium dioxide, titanium dioxide-coated mica and talc, fluoroite, apatite, perlite, boron nitride and the like. To a lesser degree, such cosmetic  
25       powders include organic materials such as nylon and polyethylene. All these materials are blended together in various levels in order to impart desired benefits such as spreadability and adherence while being smooth, lustrous and of high covering power.

Titanium dioxide, or  $\text{TiO}_2$  is well known for use in the art as a filler or extender. Japanese Patent Application 62-16410, published January 24, 1987, Pola Kasei Kogyo KK, discloses a  
30       combination of plate-like powders and globular  $\text{TiO}_2$  having an average diameter 1-50 microns compounded in a solid cosmetic composition at a level from about 1% to 85%. Said cosmetic compositions are reputed to have excellent adherence to and smoothly spread on the skin. Japanese Patent Application 62-181210, published August 8, 1987, Pola Kasei Kogyo KK, discloses solid  
cosmetic compositions comprising 10 to 85% of a base agent comprising plate shaped powders such  
35       as mica and talc with  $\text{TiO}_2$  having average grain size of 1-50 microns in a ratio of powder to  $\text{TiO}_2$  of 1: 9 to about 9.5: 0.5. The cosmetic compositions disclosed therein are reputed to have good adhesion and removal, good spread ability and good skin feel. Korean Patent Application 91-

- 03133, published May 18, 1991, Lucky Company, discloses make-up compositions containing powders obtained by adsorbing 10-40% by weight of  $\text{TiO}_2$  onto mica. Said treated mica is combined with 0.5-20% focus powders to form a emulsified foundation composition. Said composition is reputed to have a good soft focus effect and an ultraviolet ray intercepting effect.
- 5 European Patent Application 0 191 292, published August 20, 1986, Sumitomo Chemical, discloses makeup compositions comprising flaky titanium oxide having a mean thickness from 0.01 to below 0.1 microns and a mean thickness of 0.1 to 3 microns and a mean size of 0.8 to 70 microns. Said compositions disclosed therein include powder foundations wherein the titanium dioxide is used as an extender (as opposed to a pigment) at levels from about 20 to 90% by weight of the composition.
- 10 Such foundations, containing about 50% titanium oxide, are reputed to be superior in terms of adherence and smooth feel to foundations containing comparable amounts of talc.

- In the present invention, good coverage and uniformity on the skin is achieved utilizing selected talcs as opposed to titanium dioxide as the filler. Minimizing or eliminating titanium dioxide as a filler is advantageous since its presence generally is responsible for whitened or ashy
- 15 look it leaves on the skin. This result is surprising based on comparison with compositions, such as pressed powders, containing high levels of non-specific talc that do not provide adequate coverage.

#### SUMMARY OF THE INVENTION

The present invention are for powder cosmetic composition comprising talc wherein said talc comprises:

- 20 a. a first talc having a particle size distribution wherein no more than about 45% of the particles are 10 microns or less; no more than about 70% of the particles are 15 microns or less and no more than 85% of the particles are 20 microns or less;
- b. a second talc having a particle size distribution wherein no less than about 55% of the particles are 10 microns or less, no less than about 80% of the particles are 15 microns or less and no less than about 90% of the particles are 20 microns or less; and
- 25 c. a sufficient amount of an sebum absorbing material which absorbs from about 0.2 grams of sebum per gram of material (g/g) to about 3.5 g/g;
- wherein the ratio of said first talc to said second talc is from about 1:1 to about 6:1.

- One object of the present invention is to provide powder compositions which deliver
- 30 significantly improved coverage and uniformity and duration of wear when applied to the skin. It is also an object of the present invention that the present invention provides compositions having a natural look to the skin, i.e. not whitened or ashy. Lastly an object of the present invention is to provide a convenient product form which delivers the benefits described above.

#### DETAILED DESCRIPTION OF THE INVENTION

##### 35 Definitions

As used here "powder cosmetic composition" refer to any cosmetic composition that has less than about 20% liquid content in its packaged form.

As used herein "pressed powder compositions" refer to any cosmetic composition whose packaged form is made by compressing the materials comprising a sufficient binder by physical means whereby a cake is formed having sufficient hardness to sustain its shape and resist crumbling. Said compositions are often formed in small shallow metal pans or godets to facilitate storage and placement into cosmetic cases.

As used herein "loose powder" refers to powder cosmetic composition absent the binder mentioned above, packaged in a loose form in cosmetic canisters. The canisters typically have a fine mesh screen over the loose powder wherein an applicator is applied to the screen to pick up the powder composition.

As used herein "powder foundations" refer to a cosmetic composition used for full face coverage similar to a cosmetic liquid foundation. The foundation provides an adherent base for other cosmetics such as blusher, rouge and powder.

As used herein "concealer" refers to a cosmetic composition used to conceal or hide imperfections on the face.

As used herein "packed density" refers to the density of the a material as measured by a Hosokawa Powder Characteristics Tester from Hosokawa Micron Corporation, Summit N.J., using the packed or packed method disclosed in The Annual Book of ASTM Standards, 1986, Section 5; incorporated herein by reference.

#### Talc

It has now been found that an improved coverage powder cosmetic composition can be achieved with high levels of talc selected based on its particle size distribution or PSD. These compositions provide coverage benefits previously not thought possible absent sufficient levels of other components such as titanium dioxide.

Talc is generally known to those skilled in the art as natural, powdered hydrous magnesium silicate. Talc can be ground into various particle sizes and acts as an anti caking agent that has a very smooth feel on the skin. Talc is available from a number of commercial suppliers such as Whittaker, Clark and Daniels Inc., South Plainfield N.J.; Cyprus Industrial Minerals Company, Englewood, CO; Presperse Inc., South Plainfield N.J.; and L.A. Salamon, Inc., Nontville, N.J.; U.S. Cosmetics, Dayville, CT; Miki America, Inc., Dayville, CT; Ultra Chemical, Inc., Red Bank, N.J.; Color Technologies, South Plainfield, N.J.; Kobo Products, Inc., South Plainfield, N.J.; Charles B. Chrystal Co., Inc., New York, N.Y. and Ecco Resources, So. Plainfield, N.J. Compositions of the present invention comprise from about 50% to about 90%, preferably from about 60% to about 85% and most preferably from about 70% to about 80% talc.

The talc of the present invention comprises a first talc and a second talc having a ratio of said first talc to said second talc from about 1:1 to about 6:1, preferably from about 2:1 to 4:1, most preferably about 3:1.

While not wishing to be bound by theory, it is believed that using a combination of

specifically sized particles promotes the coverage benefits found in the present invention. For example, large or coarse particle talc contributes towards providing uniformity and spreadability on the skin, however, they do not provide sufficient coverage. On the other hand, smaller or fine particle talc provide good coverage while not providing satisfactory uniformity. Therefore, the key is to combine talcs having particle size distributions or PSD's to form a poly-modal talcs which pack efficiently wherein the fine particles fit within the interstices formed between the larger particles.

As used herein particle size distribution or "PSD" refers to the particle size distribution data obtained by laser diffraction methodology using a Hariba LA-900 particle size analyzer (volume-weighted analysis of distribution). The distribution data are based on the cumulative percent of the particles which are less than a designated micron sizes. In the present invention the first talc being coarse has a PSD wherein no more than about 45%, preferably no more than about 40% and most preferably no more than about 35% of the particles are 10 microns or less; no more than about 70%, preferably no more than about 65% and most preferably no more than about 60% of the particles are 15 microns or less and no more than about 85%, preferably no more than about 80% and most preferably no more than 75% of the particles are 20 microns or less. The second talc of the present invention being fine has a PSD wherein no less than about 55%, preferably no less than about 60% and most preferably no less than about 65% of the particles are 10 microns or less; no less than about 80%, preferably no less than about 85% and most preferably no less than about 90% of the particles are 15 microns or less and no less than about 90%, preferably no less than about 95% and most preferably 100% of the particles are 20 microns or less.


It is also preferred that the talcs have packed densities from about 0.1 g/cc<sup>3</sup> to about 1.5 g/cc<sup>3</sup>, wherein the packed density of said first talc is greater than the packed density of said second talc. It is more preferred that the packed density of the first talc is from about 0.3 g/cc<sup>3</sup> to about 1.2 g/cc<sup>3</sup>, preferably from about 0.5g/cc<sup>3</sup> to about 0.9g/cc<sup>3</sup> and the packed density of the second talc is from about 0.1 g/cc<sup>3</sup> to about 0.7g/cc<sup>3</sup>, preferably from about 0.2g/cc<sup>3</sup> to about 0.4g/cc<sup>3</sup>.

It has also been discovered that the talc used in the present invention is preferably talc that has been treated with hydrophobic material. Said hydrophobic materials are applied to the surface of talc in order to impart hydrophobicity to said talc. Improvements to the composition in terms of skin adhesion and improved binding characteristics are attributable to such treatment. It is preferred that the compositions of the present invention comprises at least about 50% talc treated with hydrophobic materials. The hydrophobic materials used to treat talcs of the present invention include silicones, fatty acids esters, surfactants such as lecithin, polyfluorocarbons, rutile titanium dioxide and other such hydrophobic material are known in the art.

Preferable hydrophobic materials used to treat talcs of the present invention are silicones having a viscosity from about 0.5 to about 20,000 centistokes (csts), preferably from about 1 to about 500 csts, most preferably from about 10 to about 100 csts. Although the silicone material of the present invention may be either volatile or non-volatile, non-volatile

materials are preferred. By "non-volatile" it is meant that the vapor pressure of said fluid is less than about 10mm Hg, preferably less than about 1 mm Hg, and most preferably less than about 0.5 mm Hg at 30°C as measured using analytical means known to those skilled in the art.

Said silicone material of the present invention include poly(organosiloxane) fluids  
5 conforming to the formula:



wherein the end groups  $R_1$  and  $R_6$  are independently selected from the group consisting of hydroxyl groups, lower alkyl groups having carbon chain lengths from about  $C_1$  to about  $C_6$  and mixtures thereof, preferably methyl groups and the non-end groups  $R_2$ ,  $R_3$ ,  $R_4$  and  $R_5$  are  
10 independently selected from methyl groups, fluoroalkyl groups, phenyl groups and mixtures thereof.

The poly(organosiloxane) fluids with non-end groups ( $R_2$ ,  $R_3$ ,  $R_4$  and  $R_5$ ) comprising methyl groups are known in the art and provide the final product with a relatively non-lipophilic character. Commercially available non-volatile silicone fluids having such non-end groups  
15 include those available from Dow Corning as the 200 Fluids, and those available from General Electric as SF-96 Series.

Silicone fluids with non-end groups comprising fluoroalkyl groups are also useful herein. It is preferable, however, that the fluorine atom is attached to alkyl groups having a  $C_3$  to  $C_8$  chain length wherein the fluorine atom is attached to said alkyl group at a  
20 point no closer than third carbon atoms from the silicone/carbon bond. Commercially available non-volatile silicone fluids having such non-end groups include those available from Dow Corning as the 1265 Fluid series, and those available from General Electric as the SF- 1153 Series, most preferred is the 1265 Fluid Series, most preferably those of having a viscosity from about 100 csts to about 350 csts.


Silicone fluids with the non-end groups comprising allyl groups are also useful in the present invention. The allyl groups which are particularly useful in the present invention are phenyl groups. Particularly useful allyl-substituted silicone fluids commercially available are available as the 556 Series from Dow Corning.

Preferable poly(organosiloxane) fluids of the present invention are selected from the  
30 group consisting of perfluoropolyether fluids, poly(dimethylsiloxane) fluids, poly(phenylmethylsiloxane) fluids, poly(fluoroalkylmethylsiloxane) fluids, the copolymers of said fluids and mixtures thereof. More preferred fluids are selected from the group consisting of perfluoropolyether fluids, poly(dimethylsiloxane) fluids, their copolymers and mixtures thereof. Most preferred are poly(dimethylsiloxane) fluids and their copolymers.

35 Said fluids are selected from the group consisting of perfluoropolyether fluids,

poly(dimethylsiloxane) fluids, poly(phenylmethylsiloxane) fluids, poly(fluoroalkylmethylsiloxane) fluids, the copolymers of said fluids and mixtures thereof. More preferred fluids are selected from the group consisting of perfluoropolyether fluids, poly(dimethylsiloxane) fluids, their copolymers and mixtures thereof. Most preferred are poly(dimethylsiloxane) fluids and  
 5 their copolymers, preferably selected from the group consisting of dimethicone, phenyl dimethicone, phenyl trimethicone and mixtures thereof.

The polyfluorocarbon materials useful in the present invention includes perfluoropolyethers of general formula:



10 wherein  $R^1$  through  $R^5$  are independent fluorine atoms, perfluoroalkyl groups, or oxyperfluoroalkyl groups; the value of  $p$ ,  $q$ , and  $r$  is at least zero; wherein the perfluoropolyether molecular weight is from about 500 to about 10,000, wherein  $P$ ,  $Q$  and  $R$  may be equal, but, not zero. A preferred perfluoropolyether is the commercially available product known as Fomblin HC-04, HC-25, and HC-R available from Montefluosu of Milano, Italy.

15 Treated talcs of the present invention are available from a number of commercial sources. Said treated talcs include PF-5 Talc, SI Talc, JA-13R and JA-46R, all available from Kobo, South Plainfield N.J.; DF-10240 available from Color Techniques, South Plainfield, N.J.; Sim 2043 available from Ecco Resources, South Plainfield, N.J.; Miki T-Uft-20 and Miki-13-ST available from Miki America, Inc., Dayville, CT.; and J-68-ST-PEG/MOD available from U. S.  
 20 Cosmetics Corporation, Dayville, CT.

#### Sebum Absorbing Materials

The present invention utilizes sebum absorbing materials in levels necessary to reduce the amount of sebum on the surface of the skin therein providing substantial long wear benefits of the cosmetic composition. To achieve sufficient sebum absorption for increased cosmetic wear  
 25 the composition comprises from about 2.0% to about 15%, preferably from about 2.0% to about 8.0%, and most preferably from about 2.0% to about 4.0% of a sebum absorbing material capable of absorbing from about 0.2 grams of sebum per gram of material (herein referred to as  $g_{\text{sebum}}/g_{\text{material}}$ ) to about  $3.5g_{\text{sebum}}/g_{\text{material}}$ , preferably from about  $0.8g_{\text{sebum}}/g_{\text{material}}$  to about  $2.6g_{\text{sebum}}/g_{\text{material}}$ , and most preferably from about  $1.5g_{\text{sebum}}/g_{\text{material}}$  to about  
 30  $2.0g_{\text{sebum}}/g_{\text{material}}$ . Compositions of the present invention containing such sebum absorbing material are able to absorb from about 0.20g of sebum per gram of the composition (herein referred to as  $g_{\text{sebum}}/g_{\text{composition}}$ ) to about  $0.35g_{\text{sebum}}/g_{\text{composition}}$ , preferably from about  $0.25g_{\text{sebum}}/g_{\text{composition}}$  to about  $0.32g_{\text{sebum}}/g_{\text{composition}}$ , and most preferably from about  $0.28g_{\text{sebum}}/g_{\text{composition}}$  to about  $0.30g_{\text{sebum}}/g_{\text{composition}}$ .

35 The method of measuring the absorption of sebum by the sebum absorbing material or



composition of the present invention is titration of a sample of said material or composition with the sebum as shown in the formulation below. Conducting the above titration is as follows:

Weigh a 1.0 gram of the sample of said material or composition into a 125 ml. metal beaker. Break up any agglomerates of the sample using a spatula (Note: agglomerates can be found in the sample itself or be formed in the beaker). Mix the sample with a Kitchen Aid™  
 5 hand mixer, (model no. KAM 5TBWH-1) equipped with the liquid blender rod illustrated in the mixer's instruction manual, at Setting 1 (lowest setting). Add the sebum to the sample while mixing until the sample is saturated. Saturation of the sample is reached when the sample completely adheres to the liquid blender rod and not to the side of the beaker, when the rotating  
 10 liquid blender rod is pressed moderately against the side wall of the beaker.

Multiplying the volume of sebum added to one gram of the sample by the density of the sebum (0.870g/ml) provides the grams of sebum per gram of material or composition titrated.

#### Sebum Formula

	<u>Component</u>	<u>Amount (% by weight)</u>
15	Mazola™ Corn Oil	7.30
	Squalene	18.80
	Oleic Acid	28.30
	Ceraphyl™ 140	45.60

Sebum absorbing materials used in the compositions of the present invention are  
 20 selected from the group consisting of starch, calcium silicate, polyethylene, nylon, boron nitride, mica, kaolin, polymer powders including natural, synthetic, and semi-synthetic cellulose, fluorocarbon resins, polypropylene, modified starches of cellulose acetate, particulate cross-linked hydrophobic acrylate or methacrylate copolymers and mixtures thereof. The hydrophobic polymer is a highly crosslinked polymer, more particularly a highly cross-linked  
 25 polymethacrylate copolymer. The material is manufactured by the Dow Corning Corporation, Midland, Michigan, USA, and sold under the trademark POLYTRAP™. Sebum absorbing materials preferred for use in the present invention include starch, calcium silicate, boron nitride and mixtures thereof, most preferably starch.

The starch used in the present invention is defined as a group of carbohydrates or  
 30 polysaccharides, of the general composition  $C_6H_{10}O_5$ , occurring as organized or structural granules of varying sizes and markings in many plant cells and hydrolyzable to several forms of dextrin and glucose. The starch found most useful in the present invention is a tapioca dextrin starch. Tapioca refers to the plant from which the starch is derived. Dextrin refers to a process  
 35 the starch has been subjected to which breaks up the relatively high molecular weight starch to form a more complicated starch structure (amylopectin) which is attracts hydrophobic materials such as sebum. Tapioca dextrin starch is commercially available from The National Starch and Chemical Company as Natrasorb Bath Starch. During processing of Natrasorb Bath Starch, the

tapioca dextrin particles which are hollow spheres, are spray dried with ammonium bicarbonate which creates "pock" marks on the starch surface increasing its surface area. This greater increases the surface area, resulting in greater sebum absorption of the starch.

#### Optional Ingredients

5 Compositions of the present invention can include numerous cosmetically acceptable ingredients selected for various desirable effects. These ingredients can be either in dry or liquid form, however, at levels that do not detract from the primary objects of the present invention.

Pigments are used in the present invention. Pigments may be selected from a large group of materials to numerous to mention herein. Included in this group are inorganic  
10 pigments, organic pigments, and pearlescent pigments. When employed, the pigments are present in proportions depending on the color and the intensity of the color which it is intended to produce. Pigments can be used in the present invention at levels from about 0.1% to about 20%, preferably from about 0.5% to about 12%. Pigments are selected from the group consisting of inorganic pigments, organic lake pigments, pearlescent pigments, and mixtures  
15 thereof. Said pigments may optionally be surface-treated with a large number of materials that include, but, not limited to silicones, perfluorinated compounds, lecithin, amino acids, lauroyl lysine, teflon, and esters. Included are the pigments as disclosed in U. S. Patents 5,368,639 and 5,458,681, both to Hasegawa et al., issued November 29, 1994 and October 17, 1995; both herein incorporated by reference. Inorganic pigments useful in the present invention include  
20 those selected from the group consisting of rutile or anatase titanium dioxide, coded in the Color Index under the reference CI 77,891; black, yellow, red and brown iron oxides, coded under references CI 77,499, 77, 492 and, 77,491; manganese violet (CI 77,742); ultramarine blue (CI 77,007); chromium oxide (CI 77,288); chromium hydrate (CI 77,289); and ferric blue (CI 77,510) and mixtures thereof.

25 The organic pigments and lakes useful in the present invention include those selected from the group consisting of D&C Red No. 19 (CI 45,170), D&C Red No. 9 (CI 15,585), D&C Red NO. 21 (CI 45,380), D&C Orange No. 4 (CI 15,510), D&C Orange No. 5 (CI 45,370), D&C Red No. 27 (CI 45,410), D&C Red No. 13 (CI 15,630), D&C Red No. 7 (CI 15,850), D&C Red No. 6 (CI 15,850), D&C Yellow No. 5 (CI 19,140), D&C Red No. 36 (CI 12,085), D&C  
30 Orange No. 10 (CI 45,425), D&C Yellow No. 6 (CI 15,985), D&C Red No. 30 (CI 73,360), D&C Red No. 3 (CI 45,430) and the dye or lakes based on Cochineal Carmine (CI 75,570) and mixtures thereof.

The pearlescent pigments useful in the present invention include those selected from the group consisting of the white pearlescent pigments such as mica coated with titanium oxide,  
35 bismuth oxychloride, colored pearlescent pigments such as titanium mica with iron oxides, titanium mica with ferric blue, chromium oxide and the like, titanium mica with an organic pigment of the above-mentioned type as well as those based on bismuth oxychloride and

mixtures thereof.

Any optional ingredients known to those skilled in the art may also be used in the invention. Examples of optional ingredients are disclosed in CTFA Cosmetic Ingredient Handbook, Second Edition, 1992, pages 621-622, 623-626 and 637-639; incorporated herein by reference.

5 Some of the more frequently used components include from about 1% to about 10% fillers and powders other than talc, including but not limited to the group consisting of treated and untreated mica, nylon, polyethylene, silica, polymethacrylate, kaolin, teflon, starch, oil absorbers and mixtures thereof. From about 1 to about 20% liquid ingredients including, but not limited to the group consisting of silicone oils; long chained fatty acid esters; glycerides; water, fragrances; skin  
10 conditioning and protective materials including, botanical or biological products as disclosed in The CTFA, Cosmetic Ingredient Handbook, Second Edition, pages 493-496; herein incorporated by reference. Other skin conditioning and protective material include, but, are not limited to panthenol, allantoin, aloe, aloe vera gel, PABA, tocopheryl; and mixtures thereof. From about 0.1% to about 2% cosmetic preservatives including, but not limited to the group consisting of  
15 methylparaben, propylparaben, butylparaben, ethylparaben, potassium sorbate, trisodium EDTA, phenoxyethanol, ethyl alcohol, diazolidinyl urea, imidazolidinyl urea, quaternium-15 and mixtures thereof.

#### Coverage Measurement

As stated above, the compositions of the present invention have improved coverage  
20 compared with conventional powder compositions known in the art. The following test determines the extent of coverage of the powder composition:

Attach several 8" x 14" strips of 100% black cotton fabric to a flat vertical surface. The fabric is model CC SLD 7018, Black, at 44 threads per inch, available from Beachwood Fabric Centers of America. The fabric strips can be cut to 5 1/2" lengths once the test is complete,  
25 facilitating its display for evaluation.

A new applicator is to be used for each sample tested. In the case of a compressed powder product, the entire surface of the product is first wiped with the applicator for 8-10 strokes until surface of cake is broken or ribbon/design mark has been removed. Twice rub in a circular motion in a circular motion across entire surface of the powder product one half of a cosmetic applicator  
30 such as a sponge or puff. In the case of a loose powder, the entire puff is dabbed five times onto the screen over the powder.

Wipe the applicator in a downward motion using even pressure on the applicator to distribute the powder over a six to seven inch length of the material disclosed above. Continue to  
35 wipe the applicator over the same area of the material for about nine more times, with no additional replenishment of product to the applicator.

The samples are evaluated for coverage and uniformity, often referred to as "payout" using a Spectraflash 500™ Spectrophotometer made by Datacolor International, Lawrenceville, N.J. The

value  $V$  is the ratio of  $K$  to  $S$  wherein  $K$  is the value of the light absorbed and  $S$  is the value for the light scattered, the light being that having a wavelength of the highest absorption value for the black fabric. The Coverage Value or  $CV$  of the sample is determined by dividing value  $V$  for the sample by the value  $V$  for the fabric. The  $CV$  of the sample is compared to standard products known to have  
 5 either desirable or non-desirable coverage and uniformity characteristics when applied to the skin.

#### EXAMPLES

The following are non-limiting of powder products which embody the present invention. Said samples contain a number of other routinely used cosmetic ingredients which is envisioned to be used in conjunction with the present invention. Said ingredients are employed to help for the  
 10 specific product form, and/or to promote secondary skin benefits such as oil control and moisturization.

##### 1. Press Powder Foundation

	Component	Amount (% by weight)
	Octyldodecyl Stearyl Stearate	4.97
15	Silicone Oil <sup>1</sup>	2.48
	Trimethyl Trimellitate	0.80
	<u>Talc</u>	
	Talc One <sup>2</sup>	52.06
	Talc Two <sup>3</sup>	19.26
20	Zinc Stearate	1.40
	Calcium Silicate	1.80
	Nylon -12	1.60
	Silica	0.50
	Bismuth Oxychloride	2.00
25	Starch <sup>4</sup>	3.00
	Methylparaben	0.20
	Propylparaben	0.10
	Sodium Dehydroacetate Monohydrate	0.12
	<u>Pigments</u>	
30	Treated Yellow Iron Oxide	0.70
	Treated Red Iron Oxide	0.59
	Treated Black Iron Oxide	0.36
	Treated Mica	5.00
	Ultramarine Blue	0.06
35	Titanium Dioxide	3.00

1 available from Dow Corning as DC 200 Fluid

2 available from US Cosmetics as J-68-ST-PEG/MOD

3 available from US Cosmetics as Miki - 13-ST

4 available from The National Starch and Chemical as Natrasorb

2. <u>Loose Powder</u>		
5	<b>Component</b>	<b>Amount (% by weight)</b>
	Octyldodecyl Steroyl Stearate	3.61
	Silicone Oil <sup>1</sup>	1.81
	Trimethyl Trimellitate	0.58
	<u>Talc</u>	
10	Talc One <sup>2</sup>	37.51
	Talc Two <sup>3</sup>	25.00
	Zinc Stearate	1.50
	Magnesium Carbonate	3.50
	Polyethylene	3.35
15	Sercite	10.00
	Calcium Silicate	1.50
	Starch <sup>4</sup>	2.25
	Methylparaben	0.20
	Propylparaben	0.10
20	Sodium Dehydroacetate Monohydrate	0.10
	Quaternium-15	0.02
	<u>Pigments</u>	
	Treated Yellow Iron Oxide	0.48
	Treated Red Iron Oxide	0.25
25	Treated Black Iron Oxide	0.24
	Treated Mica	5.00
	Titanium Dioxide	3.00

1 available from Dow Corning as DC 200 Fluid

2 available from Color Techniques as DF-10240

30 3 available from Kobo as A-CL3

4 available from Cosmetic Specialties as Buffalo Starch

3. <u>Pressed Powder</u>		
35	<b>Component</b>	<b>Amount (% by weight)</b>
	Octyldodecyl Steroyl Stearate	0.50
	Silicone Oil <sup>1</sup>	3.50
	Dimethicone and Trimethylsiloxysilicate	2.75

	C <sub>12</sub> -C <sub>15</sub> Alkyl Benzoate	0.50
	Coco-Caprylate/Caprate	2.20
	<u>Talc</u>	
	Talc One <sup>2</sup>	45.50
5	Talc Two <sup>3</sup>	19.50
	Zinc Stearate	2.50
	Polyethylene	3.00
	Kaolin	2.00
	Starch <sup>4</sup>	5.00
10	Methylparaben	0.20
	Propylparaben	0.10
	Ethylparaben	0.10
	<u>Pigments</u>	
	Treated Yellow Iron Oxide	0.80
15	Treated Red Iron Oxide	0.31
	Treated Black Iron Oxide	0.14
	Treated Mica	10.00
	Titanium Dioxide	1.40
	1 available from Dow Corning as DC 200 Fluid	
20	2 available from US Cosmetics as Soft Talc	
	3 available from US Cosmetics as LI TA 13R	
	4 available from The National Starch and Chemical as Dry Flo	

	4. Pressed Powder	
25	Component	Amount (% by weight)
	Octyldodecyl Steroyl Stearate	5.00
	Silicone Oil <sup>1</sup>	1.00
	<u>Talc</u>	
	Talc One <sup>2</sup>	48.30
30	Talc Two <sup>3</sup>	20.45
	Zinc Stearate	2.50
	Polyethylene	3.00
	Calcium Silicate	1.00
	Micro Sponge Powder <sup>4</sup>	4.00
35	Botanical Oil <sup>5</sup>	2.00
	Methylparaben	0.20
	Propylparaben	0.10

	Imidazolidinyl Urea	0.10
--	---------------------	------

Pigments

	Treated Yellow Iron Oxide	0.11
	Treated Red Iron Oxide	0.80
5	Treated Black Iron Oxide	0.02
	Treated Ultramarine Blue	0.02
	Treated Mica	10.00
	Titanium Dioxide	1.40

- 1 available from Dow Corning as SF-96-350 type
- 10 2 available from US Cosmetics as Soft Talc
- 3 available from US Cosmetics as LI TA 13R
- 4 available from Dow Corning as Polytrap
- 5 available from Bush Boake Allen, as Essential Oil 103-06.

Process Method

- 15 Mix all the powdery or dry materials in powder blender, such as a Lodge mixer until homogeneous. Pulverize this mixture in a standard hammer mill, such as Micropul single hammer mill, equipped with a 0.010" herringbone screen. Return the mixture to the powder blender. Mix at ambient temperature all the liquid ingredients in a vessel equipped with a mixer, such as a Lighting Mixer until homogeneous. Spray the liquid mixture onto the powdery mixture in the powder
- 20 blender and mix about 10 minutes. Stop the powder blender, scrape side walls and mix for about 5 minutes. Sift the resulting granulation through a 0.032" screen and place into storage bins. In the case of pressed powders, compress the granulation into various shaped standard makeup pans or godets using a ribbon punch press, such as a Hydraulic Kemwall Press, at a compression pressure wherein the pressed powder can sustain physical insult when exposed to routine quality testing such
- 25 as a drop test which is routinely used in the art. Insert the pans in appropriate cosmetic cases.


In the case of loose powders, appropriate canisters are filled with the granulation from the storage bins using for example a volumetric filler such as Master or All-fill feeders.

## WHAT IS CLAIMED IS:

1. A powder cosmetic composition comprising talc wherein said talc comprises:
  - a. a first talc having a particle size distribution wherein no more than 45%, preferably no more than 40%, and most preferably no more than 35% of the particles are 10 microns or less; no more than 70%, preferably no more than 65%, most preferably no more than 60% of the particles are 15 microns or less; and no more than 85%, preferably no more than 75% and most preferably no more than 70% of the particles are 20 microns or less; and
  - b. a second talc having a particle size distribution wherein no less than 55%, preferably no less than 60%, and most preferably no less than 65% of the particles are 10 microns or less; no less than 80%, preferably no less than 85% and most preferably no less than 90% of the particles are 15 microns or less; and no less than 90%, preferably no less than 95% and most preferably no less than 100% of the particles are 20 microns or less; and
  - c. a sufficient amount of an sebum absorbing material capable of absorbing from 0.2 grams of sebum per gram of material ( $\text{gsebum/gmaterial}$ ) to  $3.5\text{gsebum/gmaterial}$ ; preferably from  $0.8\text{gsebum/gmaterial}$  to  $2.6\text{gsebum/gmaterial}$ ; most preferably from  $1.5\text{gsebum/gmaterial}$  to  $2.0\text{gsebum/gmaterial}$ ;wherein the ratio of said first talc to said second talc is from 1:1 to 6:1, preferably 2:1 to 4:1, and most preferably 3:1.
2. A powder cosmetic composition according to claim 1 wherein the first and second talc have packed densities from  $0.1\text{ g/cm}^3$  to  $1.5\text{ g/cm}^3$  wherein the packed density of said first talc is greater than the packed density of said second talc; preferably wherein the first talc has a packed density is from  $0.3\text{g/cm}^3$  to  $1.2\text{ g/cm}^3$ , preferably  $0.5\text{ g/cm}^3$  to  $0.9\text{ g/cm}^3$  and the second talc has a packed density from  $0.1\text{ g/cm}^3$  to  $0.7\text{ g/cm}^3$ , preferably  $0.2\text{ g/cm}^3$  to  $0.4\text{ g/cm}^3$  wherein the packed density of said first talc is greater than the packed density of said second talc.
3. A powder cosmetic composition according to claim 1 through 2 comprising from 50% to 90%, preferably from 60% to 85%, most preferably from 70% to 80% talc and from 2.0% to 15% , preferably from 2.0% to 8.0% and most preferably from 2.0% to 4.0% sebum absorbing material.



4. A powder cosmetic composition according to claim 3 wherein the sebum absorbing materials is selected from the group consisting of starch, calcium silicate, polyethylene, nylon, boron nitride, mica, kaolin, polymer powders including natural, synthetic, and semi-synthetic cellulose, fluorocarbon resins, polypropylene, modified starches of cellulose acetate, particulate cross-linked hydrophobic acrylate or methacrylate copolymers and mixtures thereof, preferably selected from the group consisting of starch, calcium silicate, polyethylene, nylon, boron nitride and mixtures thereof and most preferably starch.
5. A powder cosmetic composition according to claim 1 through 4 wherein the composition comprises at least 50% talc treated with hydrophobic materials; preferably hydrophobic material selected from the group consisting of silicone, fatty acid esters, lecithin, polyfluorocarbons, rutile titanium dioxide and mixtures thereof; most preferably silicone.
6. A powder cosmetic composition according to claim 4 wherein the silicone is a poly(organosiloxane) fluids conforming to the formula:



wherein the end groups  $R_1$  and  $R_6$  are independently selected from the group consisting of hydroxyl groups, lower alkyl groups having carbon chain lengths from  $C_1$  to  $C_6$  and mixtures thereof, preferably methyl groups; and the non-end groups  $R_2$ ,  $R_3$ ,  $R_4$  and  $R_5$  are independently selected from methyl groups, fluoroalkyl groups, phenyl groups and mixtures thereof.

# INTERNATIONAL SEARCH REPORT

International Application No  
PCT/US 96/12247

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 6 A61K7/035

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)  
IPC 6 A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP,A,0 587 415 (UNILEVER PLC) 16 March 1994 see the whole document ---	1
A	DATABASE WPI Week 8943 Derwent Publications Ltd., London, GB; AN 89-310020 XP002019201 & DD,A,268 157 (VEB BERLIN-KOSMETIK) , 24 May 1989 see abstract ---	1
A	EP,A,0 282 823 (KAO CORPORATION) 21 September 1988 see the whole document -----	1

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

\*A\* document member of the same patent family

Date of the actual completion of the international search

22 November 1996

Date of mailing of the international search report

06.12.96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl.  
Fax (+ 31-70) 340-3016

Authorized officer

Couckuyt, P

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 96/12247

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-587415	16-03-94	AU-B- 671847	12-09-96
		AU-A- 4619593	17-03-94
		CA-A- 2104993	11-03-94
		JP-A- 6192038	12-07-94
		NZ-A- 248534	28-03-95
		ZA-A- 9306551	06-03-95
-----			
EP-A-282823	21-09-88	JP-B- 1038763	16-08-89
		JP-C- 1553824	04-04-90
		JP-A- 63230612	27-09-88
		US-A- 4885109	05-12-89
-----			

**THIS PAGE BLANK (USPTO)**